



ASSYST sprl / A.S.O.W. sprl  
Hellegatstraat 13a - 2590 Berlaar - Belgium  
Tel: +32 495 50 61 14 / +32 496 83 70 27  
Website: [www.assyst.org](http://www.assyst.org) / [www.artsuppliesonweb.com](http://www.artsuppliesonweb.com)  
Email: [ao@assyst.org](mailto:ao@assyst.org) / [vera.opsommer@assyst.org](mailto:vera.opsommer@assyst.org)

## MODELLING WAX

### **DESCRIPTION:**

Our modelling waxes are a composition of different oil derivatives and natural resins. The waxes are specially formulated to make it as comfortable as possible for the artist and are colored with a brown aniline to see all the details.

### **There are 3 different hardnesses:**

Modelling wax 130 (soft)	Average melting point: 51°C
Modelling wax 103 (medium)	Average melting point: 54°C
Modelling wax 210 (hard)	Average melting point: 59°C

The waxes need to be heated in a bain-marie and can then be modelled easily.

### **Storage:**

You can store the wax indefinitely in a cool and dry place.