



ASSYST sprl / A.S.O.W. sprl
 Hellegatstraat 13a - 2590 Berlaar - Belgium
 Tel: +32 495 50 61 14 / +32 496 83 70 27
 Website: www.assyst.org / www.artsuppliesonweb.com
 E-mail: ao@assyst.org / vera.opsommer@assyst.org

NATURAL BRONZE POWDER

DESCRIPTION:

Tin bronze 89/11 spherical AK < 0,063 mm.

THIS PRODUCT HAS BEEN TESTED AND THE FOLLOWING RESULTS HAVE BEEN OBTAINED:

Inspection function	Unit	Actual value	Minimum value	Maximum	Setting point
Sieve analysis ISO 4497 Class of residues					
> 63 µm	%	0,1	-	5,0	
< 63 µm	%	99,9	95,0	-	
Filling density ISO 3923/1	g/cm ³	5,00			4,60
Chemical analysis :					
Tin (Sn)	%	10,4	10,0	11,5	
Phosphorus (P)	%	0,32	0,27	0,43	
Copper (Cu)	%	Rest	Rest	Rest	