



ASSYST sprl / A.S.O.W. sprl  
 Hellegatstraat 13a - 2590 Berlaar - Belgium  
 Tel: +32 495 50 61 14 / +32 496 83 70 27  
 Website: [www.assyst.org](http://www.assyst.org) / [www.artsuppliesonweb.com](http://www.artsuppliesonweb.com)  
 Email: [ao@assyst.org](mailto:ao@assyst.org) / [vera.opsommer@assyst.org](mailto:vera.opsommer@assyst.org)

## IMITATION BRONZE POWDER: RICH PALE GOLD

### DESCRIPTION:

Bronze Flake Powder, based on a copper-zinc alloy, for effect pigment applications

### CHARACTERISTICS:

Inspection Criteria	Unit	Lower limit value	Upper limit value	Test Method
Particle size distribution				
D10	µm	13	18	LCI.020.0
D50	µm	35	46	LCI.020.0
D90	µm	68	90	LCI.020.0
Apparent density	g/cm <sup>3</sup>	0.60	1.30	LCI.018.0
Covering capacity	cm <sup>2</sup> /g	2400	3400	LCI.001.0