



ASSYST sprl / A.S.O.W. sprl  
Hellegatstraat 13a - 2590 Berlaar - Belgium  
Tel: +32 495 50 61 14 / +32 496 83 70 27  
Website: [www.assyst.org](http://www.assyst.org) / [www.artsuppliesonweb.com](http://www.artsuppliesonweb.com)  
Email: [ao@assyst.org](mailto:ao@assyst.org) / [vera.opsommer@assyst.org](mailto:vera.opsommer@assyst.org)

## CHAVANT MONU-MELT

### **DESCRIPTION:**

Monu-Melt™ brings all of the qualities of Clayette™ – a sulfur-free, non-hardening, tack-free, odor-free, and flexible clay – into a formula that can be melted and applied to a CNC foam armature by brush. By popular demand this material has been introduced in a Dark Forest Green color.

### **UNIQUE PROPERTIES:**

Monu-Melt™ will not oxidize and can be left out or heated and cooled repeatedly without any significant change. Will not dry or crack.

### **PHYSICAL PROPERTIES:**

Density: 96.7 lbs./cu. ft.  
Specific Gravity: 1.55 g/cm

### **SOFTENING POINT:**

Monu-Melt™ should be melted in a range from 82°C-93°C/180-200°F. Keeping the clay above 93°C/200°F will result in bubbling of the liquid clay. This bubbling is mostly aesthetic, and will not affect the characteristics of the cool clay.

### **WORKING TEMPERATURE:**

Room temperature.

### **HYGIENE:**

Wash hands with soap and water after use.